

JM DEXCELL® GLASS-MAT ROOF BOARD

Coated Glass-Mat Faced Gypsum Cover Board


Meets the requirements of ASTM C 1177

Features and Components

Handleability: Coated fiberglass facer ideal for mechanically fastened systems improves handling and strength. Scores and snaps easily.

Fire Performance: FM Class 1 for fire barrier requirements and UL Class A unlimited slope with excellent surface burning characteristics. 5/8" thickness meets the requirements of Type X per ASTM C 1177.


Moisture and Mold Resistance: Enhanced mold resistant core and coated fiberglass facers provide mold and mildew resistance per ASTM-D 3273.





Single Ply





System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

CA = Cold Applied

| SBS | | | | 골 | TP0 | | PVC | | EPDM | | |
|---------------------------|----|----|----|-------------|-------------|------------|--------------|----------------|-------------|-----------|-------------|
| 4 | CA | HW | SA | gle | MF | FA | MF | FA | MF | FA | BA |
| ly systems | | | | ı≅ | | Compatible | with the se | elected Sin | gle Ply sys | tems abou | re |
| HW = Heat Weldable SA = 3 | | | | Self Adhere | d MF | = Mechanic | cally Fasten | ed FA = | Fully Adhe | ered BA | = Ballasted |

Peak Advantage® Guarantee Information

| Systems | Guarantee Term* |
|--------------------------------------|---------------------|
| When used in most single ply systems | 10. 15. or 20 years |

^{*} Contact JM Technical Services for specific systems or terms over 20 years.

Codes and Approvals

Key: HA = Hot Applied







Installation/Application



Mechanically Fastened

Refer to the Application Guides and Detail Drawings for instructions.

Packaging and Dimensions

| Size | 4' x 4' (1.22 m x 1.22 m) | | | | | |
|--------------------|--|--|--|--|--|--|
| Thickness, nom | 1/4" (6.4 mm) | ½" (12.7 mm) | 5/4" (15.9 mm) | | | |
| Weight/Board, nom | 19 lb (8.6 kg) | 32 lb (14.5 kg) | 40 lb (18.2 kg) | | | |
| Coverage/Pallet | 960 ft ² (89 m ²) | 768 ft ² (71 m ²) | 704 ft ² (65 m ²) | | | |
| Boards/Pallet | 60 | 48 | 44 | | | |
| Pallet Weight | 1,200 lb (544 kg) | 1,612 lb (731 kg) | 1,964 (891 kg) | | | |
| Pallets per Truck* | 40 | 30 | 24 | | | |
| Size | 4' x 8' (1.22 m x 2.44 m) | | | | | |
| Thickness, nom | 1/4" (6.4 mm) | ½" (12.7 mm) | 5/s" (15.9 mm) | | | |
| Weight/Board, nom | 38 lb (17.2 kg) | 64 lb (29.0 kg) | 80 lb (36.3 kg) | | | |
| Coverage/Pallet | 1408 ft ² (131 m ²) | 960 ft ² (89 m ²) | 960 ft ² (89 m ²) | | | |
| Boards/Pallet | 44 | 30 | 30 | | | |
| Pallet Weight | 1760 lb (798 kg) | 2016 lb (914 kg) | 2678 lb (1215 kg) | | | |
| Pallets per Truck* | 27 | 24 | 18 | | | |
| Producing Location | Waukegan IL, Savannah, GA | | | | | |

^{*} Assumes 48' flatbed truck.

DEXcell® is registered trademark of National Gypsum Company. DEXcell® is manufactured by National Gypsum Company and is marketed by Johns Manville as JM® DEXcell®.

Note: Technical information on this data sheet is intended to be used as a general guideline only and is subject to change without notice. Contact your JM Sales Representative for further details.



JM DEXCELL® GLASS-MAT ROOF BOARD

Coated Glass-Mat Faced Gypsum Cover Board

Meets the requirements of ASTM C 1177

Typical Physical Properties

| Test | | ASTM | JM DEXcell Glass-Mat Roof Board | | | | |
|--------------|---|--------|---------------------------------|-----------------------|--------------|--|--|
| | | ASTW | 1⁄4" (6.35 mm) | ½" (12.7 mm) | %" (15.9 mm) | | |
| ≘ | Compressive Strength, psi (kPa), nom | C 473 | 900 (6,205) | | | | |
| Strength | Flexural Strength, lb, parallel, min | C 473 | 40 | 80 | 100 | | |
| ॐ | Bending Radius, ft (m), max | NA | 4 (1.2) | 6 (1.8) | 8 (2.4) | | |
| are | Moisture Vapor Permeance, perms (ng/(Pa•s•m²), max | E 96 | 25 (1,429) | 24 (1,371) | 23 (1,314) | | |
| Moisture | Water Absorption, % by wt, max | C 1177 | 10 | | | | |
| 2 | Mold Resistance | D 3273 | 10 | | | | |
| Installation | Flute Span, in (cm), max | E 661 | 2 % (6.7) | 5 (12.7) | 8 (20.3) | | |
| | Weight, lb/ft² (kg/m²), nom | NA | 1.2 (5.9) | 2.0 (10) | 2.5 (12) | | |

Thermal Performance

| Thick | cness | | Nominal R-Value (Resistance) | | |
|-----------------|-------|------|---------------------------------|---------|--|
| in. | mn | 1 | (hr•ft²•°F)/BTU | m²•°C/W | |
| 1⁄4 | 6.4 | | 0.32 | 0.056 | |
| ½ 12.7 | | 7 | 0.45 | 0.079 | |
| 5/8 | 15.9 | 9 | 0.56 | 0.099 | |
| Test | | ASTM | JM DEXcell Glass-Mat Roof Board | | |
| Flame Spread | | E 84 | 0 | | |
| Smoke Developed | | E 84 | 0 | | |